



KEMCO GUM Jointing compound

Application area

- For connection and construction joints (up to 20 mm) on wood, plastic, mineral substrates or glass indoors and outdoors

Features

- UV- and weather-resistant
- Ready for use
- Strong adhesive
- Elastic
- Suitable to receive further waterproofing and surfacing coats
- Suitable to receive paint and coloured surfacing coats
- Resin base: Polyurethane resin

Pack sizes

310 ml cartridges

12 cartridges / carton

Storage

Avoid direct sunlight and frost!

See label for use before date.

Store in closed original containers in dry rooms at temperatures between +5°C and +25°C.

Allow the material to stabilize to between +18°C and +20°C for at least 24 hours prior to use.

See label for use before date.

Consumption

min. 310 ml / 3 cm (joint width 1x1 cm)

Properties

Colour	Grey
Cured after *	approx. 1 d

* Values obtained at a temperature of 23 °C - 50% rel. humidity. These values vary depending on the weather conditions, such as wind, humidity and temperature.

Application

Substrates must be dry, firm and free from contaminants which may affect adhesion and must be prepared accordingly.

Material, ambient air and substrate temperature must be at least +5°C to max. +30°C with a relative humidity < 80%. When executed, the surface temperature must be 3 K above the dew point.

For porous substrates, such as concrete, screed, aerated concrete blocks, wood-based materials, etc., before processing the KEMCO GUM Jointing compound with KEMCO 1K Primer, KEMCO POX 2K Primer or COELAN Primer EP Plus they should be primed.

Remove the aluminum cover. Pierce the protective membrane in the upper threaded part over its entire surface. Now unscrew the plastic nozzle and cut off diagonally, depending on the desired application thickness. Use the cartridge in the hand gun and in the compressed air gun (2-4 bar). Before starting the work, it is essential to check the joints to be filled, for their suitability and eliminate any possible causes of deficiencies. Trapped moisture can cause blistering and detaching. KEMCO GUM Jointing compound may only have a 2-flank adhesion during processing. Avoid a three-point adhesion by filling the joint with backfill material (z.B. PE round rubber cord).

Personal protective equipment must be worn.

GISCODE

PU40

Disposal

Liquid	EAK 08 05 01
cured	EAK 17 02 03

General information

The times given above are reduced with higher and increased with lower ambient and substrate temperatures. KEMPER SYSTEM products must not be mixed with other manufacturers' products.

Only for commercial use.

Our technical data sheets / technical information and application instructions reflect the current level of knowledge in our company and the experience with our products. In each case, the new edition supersedes the previous technical information and renders it invalid. It is therefore necessary that you always have to hand the current code of practise. The latest version can be retrieved from the KEMPER SYSTEM Login section. When using our products, a detailed, object-related and qualified inspection is required in each individual case in order to determine whether the product and /or application technology in question meets the specific requirements and purposes. We are liable only for our products being free from faults, and this only if our relevant product has been used and applied according to



COELAN®

the instructions in our technical data sheets. Correct application of our products therefore falls entirely within the scope of liability and responsibility of the user (contractor). Our products are sold exclusively on the bases of our conditions of sale and delivery.

Issued: Vellmar, 2023-03-30